

QUALITY STANDARDS MANUAL

FQSM G-101: 2012



Federation of Safety Glass

Created: May 2012 | Version 1 | Revision 0

Foreword

Although use of glass has increased tremendously during the last decade and a half, yet the building professionals and consumers alike are not aware of the types of value-added glass and their respective advantages. Lack of knowledge about application of various types of safety glasses and the price sensitivity of Indian consumers are yet another reason for non-acceptance of safety glasses, particularly in the residential sector.

Another dire problem facing the value-added glass industry is the lack of Indian codes, guidelines and awareness about the International codes for the selection and use of products with defined quality parameters.

Federation of Safety Glass has voluntarily brought out this *Quality Standards Manual (FQSM G-101: 2012)* for ready reference for the Manufacturers, Design Consultants and Construction Engineers to ensure sustainability of glass in the Built Environment. The consolidated references to both Indian and International Codes included in this Manual will be of immense value to the Building Professionals.

I appreciate the efforts of the FOSG for bringing out this Manual. I am sure this Manual will be quite useful to the Architects, Engineers and Builders from both the Government and the private sector in general, and the consumer in particular, and would facilitate them to select the right type of glass for different applications in the building infrastructure to meet with the architectural, structural and safety requirements.

D. S. Sachdev

*Former Director General (Works), Central Public Works Department
New Delhi
July 2012*

Preface

The *Quality Standards Manual* prepared by FOSG, fulfills an acute need in the market for clarity on acceptance criterion for various glass types and processed glass products.

The criterion specified are based on internationally accepted parameters and occasionally surpass them where technical improvements have made achieving higher quality control possible. The quality parameters specified in the manual will help standardize expectations, will help improve quality, and reduce unnecessary doubts and conflicts. The manual will help everyone, the client, the specifier, the installer and the manufacturer.

CCPS having worked with FOSG in developing these standards, will continue to participate in wider dissemination and will take feedback from the user community and work to keep the manual updated and relevant.

We also believe this initiative will give the confidence and motivate other similar industry bodies to come forward and also develop standards that will help reduce ambiguity and improve clarity.

FOSG's effort in bringing out the document and having its members agree to conform to these standards heralds a new chapter in industry led responsible initiatives.

Deepak Gahlwt

Architect & Hon. Convener, CCPS

New Delhi

July 2012

Acknowledgements

The *Quality Standards Manual* is a result of exceptional teamwork Mr. Sharanjit Singh, Mr. Tariq Kachwala, Mr. Vivek Dubey & Mr. Prem Dutt as FOSG members as well as Mr. Deepak Gahlowt and Mr. Shashi Kant of Confederation of Construction Products & Services (CCPS) who worked closely to develop this comprehensive manual.

The *Quality Standards Manual* developed jointly by FOSG and CCPS will serve the purpose of an acute need for clarity on acceptance criterion for various types of processed glass products. Once adopted, with the quality parameters specified, it will help standardize expectations, improve quality and resolve disputes and conflicts with buyers since it will have common acceptance norms and quality standards for the entire glass industry in India.

Last but not the least I would like to thank the members for their valuable contributions given which helped in the development of this magnificent manual and special thanks to Mr. Tariq Kachwala, for devoting his precious time and efforts for giving the manual a final shape.

We will look forward for comments and suggestions for improvements in days to come.

Gurmeet S Singh

Chairman, Federation of Safety Glass

New Delhi

July 2012

Contents

1. Definitions	9
1.1 Glass Types	9
1.1.1 Annealed Glass	9
1.1.2 Tinted Glass	9
1.1.3 Coated Float Glass	9
1.1.4 Self Cleaning Glass	9
1.1.5 Anti Reflective Glass	9
1.1.6 Extra Clear Glass	9
1.1.7 Toughened/Tempered Glass	9
1.1.8 Heat Strengthened Glass	9
1.1.9 Heat Soaked Glass	9
1.1.10 Laminated Glass	10
1.1.11 Insulated glass	10
1.1.12 Sandblasted Glass	10
1.1.13 Etched Glass	10
1.1.14 Lacquered Glass	10
1.1.15 Ceramic Glass	10
2. Float Glass	11
2.1 Manufacturing Process	11
2.2 Quality Parameters	11
2.2.1 Thickness	11
2.2.2 Dimensions	11
2.2.3 Diagonals	11
2.2.4 Glass Edge Finish	11
2.2.5 Warpage and Bow	12
2.2.6 Surface and Body Defects	12
2.2.6.1 Scratches	12
2.2.6.2 Bubbles / Spots / Stones	12
3. Coated Glass	13
3.1 Basic Definitions	13
3.1.1 Coated Glass	13
3.1.2 Coating	13
3.1.3 On-Line Coating	13
3.1.4 Off-line Coating	13
3.1.5 Additive Methods of Deposition	13
3.2 Definitions of Appearance Defects	13
3.2.1 Uniformity Defect	13
3.2.2 Stain	13
3.2.3 Punctual Defect	13

3.2.3.1 Spot.....	13
3.2.3.2 Pinhole	13
3.2.3.3 Scratch.....	13
3.3 Appearance.....	13
3.3.1 General	13
3.3.2 Detection of Defects.....	13
3.3.3 Conditions of Examination.....	13
3.3.3.1 General.....	13
3.3.3.2 Uniformity Defects and Stains	14
3.3.3.3 Punctual Defects.....	14
3.3.4 Acceptance Criteria of Coated Glass Defects.....	14
4. Toughened / Tempered Glass	15
4.1 Manufacturing Process	15
4.2 Quality Parameters	15
4.2.1 Thickness	15
4.2.2 Dimensions and Squareness.....	15
4.2.3 Holes and Cutouts.....	15
4.2.3.1 Hole Dimensions	15
4.2.3.2 Hole and Cutout Location.....	15
4.2.4 Glass Edge Finish	15
4.2.5 Flatness	15
4.2.5.1 General Information.....	15
4.2.5.2 Measurement of Overall Bow.....	16
4.2.5.3 Warpage and Bow Tolerances	16
4.2.5.3.1 Overall Bow Tolerances	16
4.2.5.3.2 Local Bow Tolerances	16
4.2.5.4 Important Considerations for Optical Distortion in Fully Toughened Glass.....	17
4.2.6 Appearance	17
4.2.7 Fragmentation Test.....	17
4.2.7.1 General.....	17
4.2.7.2 Test Procedure	17
4.2.7.3 Assessment of Fragmentation	17
4.2.7.4 Minimum Values from the Particle Count.....	18
4.2.8 Stress Measurement Test	18
4.2.8.1 General.....	18
4.2.8.2 Test Procedure	18
4.2.8.3 Assessment of Measurements	19
4.2.9 Marking	19
4.3 Other Physical Characteristics	19
4.3.1 Anisotropy (Iridescence)	19
4.3.2 Spontaneous Breakage due to Nickel Sulphide Inclusions.....	19
5. Heat-Strengthened Glass	21

5.1 Manufacturing Process	21
5.2 Quality Parameters	21
5.2.1 Thickness	21
5.2.2 Dimensions and Squareness	21
5.2.3 Holes and Cutouts	21
5.2.3.1 Hole Dimensions	21
5.2.3.2 Hole and Cutout Location	21
5.2.4 Glass Edge Finish	21
5.2.5 Flatness	21
5.2.5.1 General Information	21
5.2.5.2 Measurement of Overall Bow	22
5.2.5.3 Warpage and Bow Tolerances	22
5.2.5.3.1 Overall bow Tolerances	22
5.2.5.3.2 Local Bow Tolerances	22
5.2.5.4 Important Considerations for Optical Distortion in Heat-Strengthened Glass	23
5.2.6 Appearance	23
5.2.7 Stress Measurement Test	23
5.2.7.1 General	23
5.2.7.2 Test Procedure	23
5.2.7.3 Assessment of Measurements	23
5.2.8 Marking	23
5.3 Other Physical Characteristics	23
5.3.1 Anisotropy (Iridescence)	23
6. Insulated Glass	25
6.1 Manufacturing Process	25
6.2 Quality Parameters	25
6.2.1 Thickness	25
6.2.2 Dimensions	25
6.2.3 Displacement / Mismatch	25
6.2.4 Glass Edge Finish	25
6.2.5 Sealant Protrusion	25
6.2.6 Appearance	25
6.3 Quality Tests for Insulated Glass Raw Materials	26
6.3.1 Delta-T Test for Desiccant	26
6.3.2 Tests for Silicon (Two-Part)	26
6.3.2.1 Butterfly Test	26
6.3.2.2 Peel Adhesion Test	26
6.3.3 Butyl Quantity Test	26
6.3.4 Tests for Finished Insulated Glass Units	26
6.3.4.1 Leakage Test	26
6.3.4.2 Dew Point Test	26
6.3.4.3 Shore A Hardness Test	26

6.4 Important Considerations for Optical Distortion in Insulated Glass	26
6.4.1 Interference Colouration	26
6.4.1.1 Brewster's Fringes	26
6.4.1.2 Newton Rings.....	26
6.4.2 Iridescence due to Heat-Treated Glasses	26
6.4.3 Glass Deflection due to Variations in Temperature and Barometric Pressure	26
6.4.4 External Condensation	27
7. Laminated Glass	28
7.1 Manufacturing Process	28
7.2 Quality Parameters	28
7.2.1 Nominal Thickness	28
7.2.2 Dimensions	28
7.2.3 Displacement.....	28
7.2.4 Glass Edge Finish	28
7.2.5 Appearance	28
7.2.5.1 Common Definitions	28
7.2.5.1.1 Spot Defects.....	28
7.2.5.1.2 Linear Defects.....	28
7.2.5.1.3 Other Defects.....	28
7.2.5.1.4 Opaque Spots.....	29
7.2.5.1.5 Bubbles.....	29
7.2.5.1.6 Foreign Bodies.....	29
7.2.5.1.7 Scratches or Grazes.....	29
7.2.5.1.8 Vents.....	29
7.2.5.1.9 Creases.....	29
7.2.5.1.10 Streaks due to Interlayer Inhomogeneity:.....	29
7.2.5.1.11 Edge Area.....	29
7.2.5.1.12 Vision Area.....	29
7.2.5.2 Test Method for Inspection	29
7.2.5.3 Defects in the Vision Area	29
7.2.5.3.1 Spot Defects in the Vision Area	29
7.2.5.3.2 Linear Defects in the Vision Area	29
7.2.5.4 Defects in the Edge Area for Framed Glasses.....	29
7.2.5.5 Vents	29
7.2.5.6 Creases and Streaks.....	29
7.2.5.7 Defects on Edge which will not be Framed.....	30
7.2.6 Tests for Finished Laminated Glass Units	30
7.2.6.1 Sampling Plan for Laminated Safety Glass.....	30
7.2.6.2 Boil Test.....	30
7.2.6.2.1 Principle.....	30
7.2.6.2.2 Procedure	30
7.2.6.2.3 Interpretation of Results.....	30

7.2.6.2.4 Acceptance Criteria.....	30
7.2.6.3 Humidity Test	30
7.2.6.3.1 Principle.....	30
7.2.6.3.2 Procedure	30
7.2.6.3.3 Interpretation of Results.....	30
7.2.6.3.4 Acceptance Criteria.....	30
7.2.6.4 Fracture and Adhesion Test	31
7.2.6.4.1 Principle.....	31
7.2.6.4.2 Procedure	31
7.2.6.4.3 Acceptance Criteria.....	31
Notes	32
Closing Note	34
References	35

1. Definitions

1.1 Glass Types

1.1.1 Annealed Glass

Float glass or annealed glass (also termed soda lime silicate glass) is a term for perfectly flat, clear glass manufactured by the float process. This process was invented in the UK by Sir Alastair Pilkington in 1959. It is the most basic type of glass available today and forms the basis for several fabricated glasses that are used in construction. Float glasses have a surface compression less than 3500psi. For the purpose of conciseness, all standard terms that follow refer to float glass only and other forms of glass are not considered.

1.1.2 Tinted Glass

Tinted glasses are manufactured by adding colorants to normal clear float glass during manufacture to achieve tinting and solar-radiation absorption properties. The color is achieved upon the addition of a mineral admixture. Tinting reduces heat and light penetration in buildings as compared with clear glasses.

1.1.3 Coated Float Glass

These are glasses (clear or tinted) that have been coated to reflect solar radiation striking the surface of the glass, thereby reducing solar heat gain. Coatings can be reflective or low-emissivity in nature and affect both the visual and the functional performance of the base glass.

1.1.4 Self Cleaning Glass

This is an ordinary float glass with a special photo-catalytic coating. It has a natural self-cleaning property. The active integrated coating on the outside of the glass absorbs the sun's ultraviolet rays. This causes a reaction on the surface which breaks down dirt and loosens it from the glass. It also has hydrophobic properties. When it rains or water is poured over it, it washes the dust off the glass, instead of leaving it on the glass surface.

1.1.5 Anti Reflective Glass

It is a normal float glass, but with a special coating that allows very little reflection of light. It offers maximum clarity at all times. It has maximum transparency and lowest light reflection rates and allows optimum viewing through the glass.

1.1.6 Extra Clear Glass

It is glass that has an extremely low content of iron, giving it a remarkably clear look. Extra clear glass (also commonly called low-iron glass or ultra-clear glass) has the property of allowing high light transmission with minimum color, resulting in brilliant optical clarity.

1.1.7 Toughened/Tempered Glass

Toughened or tempered glass is produced when float glass panels are heated and then cooled rapidly in a controlled

environment. This process makes the glass several times stronger than regular glass. It also makes it safer because when broken it yields small pebble-like fragments. In the heat treating process, the annealed glass is subjected to a special heat-treatment in which it is heated to about 650°C and afterwards cooled. During the quenching operation the surface of the glass cools quicker than the interior of the glass so that the residual compression stress is locked into the surface of the glass. These residual compression stresses must be overcome before the glass can fracture due to tensile stresses. The strength of the glass is determined by whether the glass is cooled rapidly or slowly.

The properties of toughened glasses are as follows:

1. Toughened glass can be as much as 5 times stronger than annealed glass. It resists breakage and can withstand temperatures between 200°C and 300°C.
2. Surface compression stress is greater than 10000 psi.
3. Unlike annealed glasses it breaks into small pieces without any sharp edges. For this reason toughened glass is classified as a safety glass.
4. Toughened glass however has a few limitations:
 - a. Once toughened, the glass cannot be cut, drilled, beveled, deep-etched or acid-treated. Therefore, all design decisions have to be taken before the glass is processed.
 - b. Tempered glass is prone to spontaneous breakage due to the presence of nickel sulfide, which cannot be completely eliminated during the float glass manufacturing process.
 - c. As it is heat-treated, it can have bows, warps and process roll distortion on the surface and this may interfere with the optics.

Toughened glass is used wherever strength is required and regular annealed glass will not be sufficient, like in high use areas like entrances, in conditions where high wind loads need to be taken by the glass surface, etc. Glass facades, sliding doors, building entrances and bath and shower enclosures are the most common uses. Fire knock-out panels, fireplace enclosures and kitchen objects like vegetable chopping board and cooking pot lids are other uses.

1.1.8 Heat Strengthened Glass

This is a particular heat treated glass that is popular for facade glazing applications like windows, vision panels and spandrel panels as well as the base material for lamination. Its mechanical strength is twice that of annealed glass and half of fully tempered glass. Surface compression is between 5000 to 8000 psi. Due to its breakage pattern, monolithic heat-strengthened glass is not classified as a safety glazing material.

1.1.9 Heat Soaked Glass

This is simply fully tempered glass that has been processed to reduce the probability of spontaneous breakage due to

nickel sulfide inclusions. Heat soaked glass has shown 98.5% reliability in tests¹. The glasses have the same advantages as fully toughened glass, but are relatively safer as the possibility of breakage is reduced.

1.1.10 Laminated Glass

This is composed of two lites of glass permanently bonded together with an interlayer material sandwiched in between. Interlayers like PVB (polyvinyl butyral) are bonded into the glass by the application of heat and pressure. Special security glass and other value-added glass can be made. The two sheets of glass may be regular float glasses, body-tinted, reflective, annealed, heat-strengthened or fully tempered glass, depending on the performance that is required. Laminated glass is a completely customizable product and can perform a wide range of functions.

Laminated glass is used as safety glazing in public buildings, commercial and retail structures, overhead glazing and large facades. It also serves as security glazing in residences, embassies, banks and combat vehicles and provides sound control in offices, institutions, malls, residences, airport, bus terminals and recording studios. Other applications include skylights, aquariums, entrance doors and glass floors².

Laminated glass offers several practical benefits and safety characteristics:

1. Safety: Laminated glass remains intact when broken, holding glass fragments in place.
2. Burglary Resistance: Laminated glass is extremely useful for security, and burglar intrusion is greatly minimized. The interlayer continues to be in place even if the glass is broken, increasing security. Ordinary glass cutters and break-in tools are not effective on laminated glass as it needs to be cut in from both the sides. In fact, laminated glass is the only glass to provide post-breakage strength.
3. Bullet-Resistance: Multiple layers of glass and interlayers provide resistance to bullet and blast resistance.
4. Sound Control: Use of regular and special interlayers can considerably reduce sound transmission. The visco-elastic properties of the interlayer have a dampening effect on noise.

1.1.11 Insulated glass

Insulated glass (IG) consists of two glass lites assembled with a space in between. This space is either left as an air gap or filled with an inert gas for better insulation. IG units offer excellent insulation from heat and have lower U-Values than monolithic glasses³. Substantial energy savings have been demonstrated from use of IG glasses as a glazing material when compared to single glazing. Often, insulated glass is used on the surface that takes the maximum direct sunlight. It is also possible to construct insulated glass units with multiple air gaps and more than 2 glass lites.

1.1.12 Sandblasted Glass

Sandblasted glass has a design or form done on it by spraying sand. This texture is rougher than the rest of the glass and it's translucent. Sand is sprayed at high velocity over the surface of the glass. The area that does not need sandblasting is kept covered during the process. The depth and degree of translucence depends on the force and type of sand used.

1.1.13 Etched Glass

Acid-etched glass is formed when regular float-glass is acid-etched on one side. Acid etching gives a uniformly smooth and satin-like effect on the glass. Such glass admits light while providing softening and vision control. An industrially produced glass ensures uniformity of coating and will not show patching.

1.1.14 Lacquered Glass

This is another kind of decorative glass meant for interior use. It is made by depositing and then baking a coat of durable and resistant lacquer to one of the glass surfaces. It is opaque in appearance and combines the advantages of glass like moisture resistance and highly aesthetic surface shine, while adding opacity.

1.1.15 Ceramic Glass

This is a tempered or heat-strengthened glass, one face of which is covered, either partially or totally, with ceramic inks. The color pigment is added while heat strengthening the glass. In addition to its decorative function, enameled glass is also a solar ray controller. It can be assembled into laminated glass or glazed insulation. It is stable, non-biodegradable and can be made into different figures and shapes. It is used for glazing and cladding in facades, skylights, canopies and floors.

¹ Please note that even after heat-soaking the probability of NiS suicide is not completely eliminated.

² In overhead glazing (skylights, canopies, etc.) and floors, use of laminated glass should be mandatory to prevent any risk of injury.

³ U-Values can be further reduced by use of low emissivity coatings.

2. Float Glass

2.1 Manufacturing Process

Float glass (also called soda lime silicate glass) is manufactured by allowing the glass from tank furnace to flow across a bath of molten tin in a controlled atmosphere of nitrogen and hydrogen which yields transparent glass sheet, the surface of which are flat and parallel so that they provide clear, undistorted vision and refraction. To know about the different quality assurance tests Annexure A may please be referred.

2.2 Quality Parameters

2.2.1 Thickness

The thickness tolerances of float glass shall be as specified in Table 2.1

Table 2.1: Thickness and Tolerance of Float Glass⁴

(All dimensions are in millimeters and as per IS14900 : 2000 (Reaffirmed 2005))

Nominal Thickness	Tolerance*
3	± 0.3
3.5	± 0.3
4	± 0.3
5	± 0.3
6	± 0.3
8	± 0.6
10	± 0.6
12	± 0.8
15	± 0.8
19	± 1.2

2.2.2 Dimensions

Tolerance on length and width of the float glass shall be in accordance with Table 2.2.

Table 2.2: Dimensional (Length or Width) Tolerance of Float Glass⁵

(All dimensions are in millimeters and as per IS14900 : 2000 (Reaffirmed 2005))

Nominal Thickness	Tolerance (Length or Width)	
	Up to and including 3 m	Above 3 m
3	+1 / -2	-
4.0	+1 / -2	-
5.0	+2 / -2	-
6.0	+2 / -2	-
8.0	+2 / -3	+3 / -4
10.0	+2 / -3	+3 / -4
12.0	+3 / -3	+4 / -4
15.0	+3 / -3	+4 / -4
19.0	+5 / -5	+6 / -6

2.2.3 Diagonals

Tolerance on diagonal of float glass shall be in accordance with Table 2.3.

Table 2.3: Diagonal Tolerance of Float Glass

(All dimensions are in millimeters and as per IS14900 : 2000 (Reaffirmed 2005))

Nominal Thickness	Tolerance (Diagonal)	
	Up to and including 3 m	Above 3 m
3	+1 / -2	-
4.0	+1 / -2	-
5.0	+2 / -2	-
6.0	+2 / -2	-
8.0	+2 / -3	+3 / -4
10.0	+2 / -3	+3 / -4
12.0	+3 / -3	+4 / -4
15.0	+3 / -3	+4 / -4
19.0	+5 / -5	+6 / -6

2.2.4 Glass Edge Finish

⁴ Glass thickness shall be measured with a micrometer or caliper which is graduated to 0.01 mm or with a measuring instrument having an equivalent accuracy.

⁵ Glass dimension shall be measured with a steel scale (tape) which is graduated to 1.00 mm. The measurement shall be made on adjacent two sides.

Edge damage usually occurs when cutting the glass (difficulty increases with thickness) and during grinding of glass. There is no standard acceptance criteria for the edge condition of the glass. Glass with edges that are severely cut, damaged or have deep, pointed shells/vents is generally not acceptable. The glass edge finish should be in accordance with Table 2.4.

Table 2.4: Glass Edge Finish

SNo.	Usage Type	Finish	Allowable Defects
1	Exposed edges	Neatly polished, straight line	Small glass fragment normally conchoidal ≤2mm
2	Silicon or butt joint	Visible line should be straight	Small glass fragment normally conchoidal ≤2mm
3	Concealed edge	Rough grinding without chips and defects	Small glass fragment normally conchoidal ≤3mm

2.2.5 Warpage and Bow

The allowed warpage and bow tolerance should be in accordance with Table 2.5

Table 2.5: Warpage and Bow Tolerance Limit

Thickness	Sizes	Tolerance%	Maximum
Upto 6mm	<3 m	0.3	6 mm
Upto 6mm	>3 m	0.3	8 mm
Above 6mm	<3 m	0.3	6 mm
Above 6mm	>3 m	0.3	10 mm

Closer tolerances may be required for glasses having thickness greater than 6 mm in butt jointed applications like partitions. This should be specified by the customer in

advance and agreed upon specifically between buyer and seller.

2.2.6 Surface and Body Defects

2.2.6.1 Scratches

Scratches shall be classified into the following categories: light, medium and heavy. The allowed scratches should be in accordance with Table 2.6.

Table 2.6: Visual Limits for Scratches

S No.	Intensity and Size	Definition	Number/ sqm
1	Light Scratch	Shall not be detectable beyond 50 cm	Any number
2	Medium Scratch (should not be more than 15.0 mm)	Visible up to 50 - 100cm, not visible beyond 100 cm	2
3	Heavy Scratch Max 10 mm	Visible up to 150cm, not visible beyond 150 cm	1

2.2.6.2 Bubbles / Spots / Stones

The allowed number of bubbles / spots / stones should be in accordance with Table 2.7.

Table 2.7: Bubbles / Spots / Stones Visual Limit

All Thicknesses	Defect Size (Diameter(d))	No of Defects
	d < 0.5mm	2/sqm
	0.5 < d < 1.0mm	1/sqm
	> 1.0mm	Nil
Observation distance 50 cm		

3. Coated Glass

3.1 Basic Definitions

3.1.1 Coated Glass

Glass substrate as defined in 2.1 to which a coating has been applied, as defined in 3.1.2 in order to modify one or more of its properties.

3.1.2 Coating

One or more thin solid layers of inorganic materials applied on to the surface of a glass substrate by various methods of deposition.

3.1.3 On-Line Coating

The treatment of the surface of a moving continuous ribbon of a basic glass, at a stage during its manufacture, before it is cut.

3.1.4 Off-line Coating

The application of a coating to individual pieces of glass within a manufacturer's or processor's premises.

3.1.5 Additive Methods of Deposition

Single or multilayer systems (consisting of metals, oxides, nitrides, fluorides or other compounds) added to the surface of the glass by different methods.

3.2 Definitions of Appearance Defects

3.2.1 Uniformity Defect

Slight visible variation in colour, either in reflection or transmission, within a coated glass pane or from pane to pane.

3.2.2 Stain

Defect in the coating larger than punctual defect, often irregularly shaped, partially of mottled structure.

3.2.3 Punctual Defect

Punctual disturbance of the visual transparence looking through the glass and of the visual reflectance looking at the glass⁶.

3.2.3.1 Spot

Defect that commonly looks dark against the surrounding coating, when viewed in transmission.

3.2.3.2 Pinhole

Punctual void in the coating with partial or total absence of coating and it normally contrasts as clear relative to the coating, when viewed in transmission.

3.2.3.3 Scratch

Variety of linear score marks, whose visibility depends on their length, depth, width, position and arrangements.

3.2.4 Cluster

Accumulation of very small defects giving the impression of stain.

3.3 Appearance

3.3.1 General

The defects affecting appearance are:

- Specific to the glass substrate (see 2.2.6), and
- Specific to the coating.

If a defect specific to the glass substrate is more visible because of the coating, it will be treated as a coating defect.

3.3.2 Detection of Defects

The defects are detected visually by an observation of the coated glass in transmission and/or reflection. An artificial sky or daylight may be used, as the source of illumination. Daylight illumination is a uniform overcast sky, without direct sunlight.

3.3.3 Conditions of Examination


3.3.3.1 General

Coated glass may be examined in stock size plates or in finished sizes ready for installation. The examination may be undertaken in the factory or on site when glazed.


The pane of coated glass being examined is viewed from a minimum distance of 3 meters. The actual distance will be dependent on the defect being considered and which illumination source is being used. The examination of the coated glass in reflection is performed by the observer looking at the side which will be the outside of the glazing. The examination of the coated glass in transmission is performed by the observer looking at the side which will be the inside of the glazing.

During the examination the angle between the normal to the surface of the coated glass and the light beam proceeding to the eyes of the observer after reflection or transmission by the coated glass shall not exceed 30° (see Figure 1).

Figure 1: Schematics of Examination Procedures




⁶ Spots, pinholes and scratches are types of punctual defects.



For panes of coated glass in finished sizes ready to be installed both the main area and an edge area of the pane shall be examined (see Figure 2)⁷.

Figure 2: Areas to be Examined on Finished Sizes Ready for Glazing



3.3.3.2 Uniformity Defects and Stains

Under the conditions of examination, given in 3.3.3.1, note any coating variations either within one pane or between neighbouring panes which are visually disturbing.

3.3.3.3 Punctual Defects

Under the conditions of examination, given in 3.3.3.1, note any spots, pinholes and/or scratches that are visually disturbing.

For spots and pinholes measure the size and note the number relative to the size of the pane. If any clusters are found, their position relative to the through vision area shall be determined.

For scratches determine whether they are in the main or edge area. Measure the length of any scratches noted. For scratches greater than 75 mm long determine the distance between adjacent scratches. For scratches less than 75 mm long note any area where their density produces visual disturbance.

3.3.4 Acceptance Criteria of Coated Glass Defects

The acceptance criteria for defects in coated glass, examined according to 3.3.3, are given in Table 3.1.

Table 3.1: Coated Glass Acceptance Criteria

DEFECT TYPES	ACCEPTANCE CRITERIA		
	Pane / Pane	Individual Pane	
		Main Area	Edge Area
Uniformity / Stain			
	Allowed as long as not visually disturbing	Allowed as long as not visually disturbing	
Spots / Pinholes			
> 3mm	Not Applicable	Not allowed	Not allowed
> 2mm and ≤ 3mm	Not Applicable	Allowed if not more than 1/m ²	Allowed if not more than 1/m ²
Clusters			
	Not Applicable	Not allowed	Allowed as long as not in area of through vision
Scratches			
> 75mm	Not Applicable	Not allowed	Allowed as long as they are separated by > 50 mm
≤ 75mm	Not Applicable	Allowed as long as local density is not visually disturbing	Allowed as long as local density is not visually disturbing

⁷ Each examination will take no more than 20 seconds.

4. Toughened / Tempered Glass

4.1 Manufacturing Process

Toughened or tempered glass is produced when float glass panels are heated and then cooled rapidly in a controlled environment. This process makes the glass stronger than annealed glass. It also makes it safer because when broken it yields small pebble-like fragments.

4.2 Quality Parameters

4.2.1 Thickness

The thickness tolerance of toughened glasses shall be in accordance with the tolerances mentioned for annealed float glasses. Please refer Table 2.1 for details.

4.2.2 Dimensions and Squareness

Tolerance limits for dimensions for rectangular glass panes are given in Figure 1 and tolerances on width and length should be in accordance with Table 4.1.

Figure 4.1: Tolerance Limits for Dimensions of Rectangular Panes




Table 4.1: Tolerances on Width B and Length H

(All dimensions are in millimeters and as per EN12150-1 June 2000)

Nominal Dimension of Side, B or H	Tolerance, t	
	Nominal Glass Thickness $d \leq 12$	Nominal Glass Thickness $d > 12$
≤ 2000	2.5	3.0
$2000 < B \text{ or } H \leq 3000$	3.0	4.0
> 3000	4.0	5.0

4.2.3 Holes and Cutouts

4.2.3.1 Hole Dimensions

The allowable hole diameter tolerance should be in accordance with Table 3.2.

Table 4.2: Tolerances on Holes

(All dimensions are in millimeters)

All Thicknesses	Hole Diameter Range	Dimensional Tolerance
	4 to 20	± 1
	21 to 100	± 2
	Above 100	Consult the Manufacturer

4.2.3.2 Hole and Cutout Location

The allowed hole and cutout location tolerance should be in accordance with Table 4.3.

Table 4.3: Tolerances on Hole and Cutout Location

(All dimensions are in millimeters)

All Thicknesses	For holes tolerance should be from centre of hole	$\pm 1.5\text{mm}$
	For cutouts tolerance should be from edge	$\pm 1.5\text{mm}$

4.2.4 Glass Edge Finish

Edge damage usually occurs when cutting the glass (difficulty increases with thickness) and during grinding of glass. There is no standard acceptance criteria for the edge condition of the glass. Glass with edges that are severely cut, damaged or have deep, pointed shells/vents is generally not acceptable. The glass edge finish should be in accordance with Table 4.4.

Table 4.4: Glass Edge Finish

SNo.	Usage Type	Finish	Allowable Defects
1	Exposed edges	Neatly polished, straight line	Small glass fragment normally conchoidal $\leq 2\text{mm}$
2	Silicon or butt joint	Visible line should be straight	Small glass fragment normally conchoidal $\leq 2\text{mm}$
3	Concealed edge	Rough grinding without chips and defects	Small glass fragment normally conchoidal $\leq 3\text{mm}$

4.2.5 Flatness

4.2.5.1 General Information

By the very nature of the toughening process, it is not possible to obtain a product as flat as annealed glass. The difference depends on the nominal thickness, the glass size dimensions and the ratio between the dimensions. Therefore a distortion known as overall bow can occur. There are two kinds of bow (see Figure 4.3):

- overall or general bow
- local bow

NOTE 1: Overall bow can, in general, be accommodated by the framing system.


NOTE 2: Local bow needs to be allowed for in the glazing materials and the weather seals. For special requirements the manufacturers should be consulted.

4.2.5.2 Measurement of Overall Bow

The pane of glass shall be placed in a vertical position and supported on its longer side by two load bearing blocks at the quarter points (see Figure 4.2). The deformation shall be measured along the edges of the glass and along the diagonals, as the maximum distance between a straight metal ruler, or a stretched wire, and the concave surface of the glass (see Figure 4.3). The measurement should be done at room temperature.


The value for the bow is then expressed as the deformation, in millimeters, divided by the measured length of the edge of the glass, or diagonal, in millimeters, as appropriate.

Figure 4.2: Support Conditions for Measurement of Overall Bow



- (1) B or H
- (2) (B or H)/2
- (3) (B or H)/4
- (4) maximum 100mm

Figure 4.3: Representation of Overall and Local Bow



- (1) deformation for calculating overall bow
- (2) B or H, or diagonal length
- (3) local bow
- (4) 300mm length

4.2.5.3 Warpage and Bow Tolerances

4.2.5.3.1 Overall Bow Tolerances

The allowed warpage or overall bow tolerance should be in accordance with Table 4.5.

Table 4.5: Overall Bow (Bend) Tolerance Limit

Thick-ness	Up to 1.2 m	1.2 to 2.5 m	2.5 to 3.05 m	3.05 to 3.66 m	Above 3.66 m
4mm	4mm	4mm	6mm	NA	-
5mm	3mm	4mm	5mm	7mm	-
6mm	3mm	4mm	5mm	7mm	-
8mm	3mm	4mm	5mm	6mm	10 mm
10mm	3mm	4mm	4mm	5mm	10mm
12mm	3mm	4mm	4mm	5mm	8mm
15mm	3mm	4mm	4mm	6mm	8mm
19mm	3mm	4mm	4mm	6mm	10mm

4.2.5.3.2 Local Bow Tolerances

Local bow can occur over relatively short distances on the edges of the glass. Local bow shall be measured over a limited length of 300mm by using a straight ruler, or a stretched wire, parallel to the edge at a distance of 25 mm from the edge of the glass (see Figure 4.3).

Local bow is expressed as millimeters / 300 mm length⁸.

The maximum allowable values for the local bow, when measured according to 4.2.5.2, for glass without holes and/or notches and/or cutouts are given in Table 4.6⁹.

Table 4.6: Maximum Values for Local Bow

Toughening Process	Local Bow mm/300 mm
Horizontal	0.5

For horizontal tempering, 200mm from either edges parallel to the roller waves shall be excluded from measurement. This method of measurement may not be applicable for non-rectangular glasses, e.g., triangles and trapezoids.

4.2.5.4 Important Considerations for Optical Distortion in Fully Toughened Glass¹⁰

1. Pressures, exerted around the periphery of glass by the glazing system, can also alter glass flatness thereby distorting reflected images. This is true regardless of whether or not the glass is heat treated.
2. Sealed insulating glass units also exhibit distortion regardless of glass type. Air or gas, trapped in the sealed airspace between the panes, expands or contracts with temperature and barometric changes, creating a pressure differential between the airspace and the atmosphere. The glass reacts to the pressure differential by being deflected inward or outward.
3. Regardless of glass flatness, the degree of reflected distortion perceived is primarily and largely due to the characteristics or symmetry of the object being reflected. Linear objects (such as building curtain walls and telephone poles) and moving objects (such as cars) may appear distorted. Irregular and free-form objects such as trees and clouds will appear to have little perceived distortion.
4. Specified bow and warp limits may not adequately define, or control, the distortion that may become apparent after glazing. The factors, noted above, may have a larger influence on the perceived reflected distortion than that which is caused by bow and warp from the heat-treating process. Consultation with suppliers and the viewing of full-size mockups, under typical job conditions and surroundings, is highly recommended for user or architectural evaluation of the reflective distortion.

4.2.6 Appearance

For surface and body defects in clear or tinted toughened glasses refer to 2.2.6.

For accepted criteria of coated toughened glasses, refer to 3.3.4 and all conditions mentioned in Section 3: Coated Glass.

4.2.7 Fragmentation Test

4.2.7.1 General


The fragmentation test determines whether the glass breaks in the manner prescribed for a thermally toughened safety float glass. Five specimens shall be tested having dimensions 360 mm x 1100 mm each, without holes, notches or cutouts.

4.2.7.2 Test Procedure

Each test specimen shall be impacted, using a pointed steel tool, at a position 13 mm in from the longest edge of the test specimen at the mid-point of that edge, until breakage occurs (see Figure 4.4)¹¹. Examples of steel tools are a hammer of about 75 gm mass, a spring loaded centre punch, or other similar appliances with a hardened point. The radius of curvature of the point should be approximately 0.2 mm.

The test specimen shall be laid flat on a table without any mechanical constraint. In order to prevent scattering of the fragments, the specimen shall be simply held at the edges, e.g. by a small frame, adhesive tape etc., so that the fragments remain interlocked after breakage yet extension of the specimen is not hindered¹².

Figure 4.4: Position of Impact Point



(1) Impact Point

4.2.7.3 Assessment of Fragmentation

The particle count and measuring of the dimensions of the largest particle shall be made between 4 minutes to 5 minutes after fracture. An area of radius 100 mm, centered on the impact point, and a border of 25 mm round the

⁸ For patterned glass, local bow shall be determined by using a straight ruler resting on the high points of the pattern and measuring to a high point of the pattern.

⁹ Source: para 4.2.8 to 4.2.8.4 from EN 12150-1 pages 9 to 12.


¹⁰ Source: para 7.4.3 to 7.4.6 from ASTM C 1048 - 04.

¹¹ The fragmentation characteristics of glass are unaffected by temperatures between -50°C and +100°C.

¹² For thermally toughened safety glass manufactured by vertical toughening, the impact point shall not be on the tong mark edge.

edge of the test specimen (see Figure 4.5), shall be excluded from the assessment.


Figure 4.5: Area to be Excluded from Particle Count



(1) Excluded Area

The particle count shall be made in the region of coarsest fracture (the aim being to obtain the minimum value). The particle count shall be made by placing a mask (50 ± 1) mm x (50 ± 1) mm on the test piece. The number of crack-free particles within the mask shall be counted. A particle is 'crack-free' if it does not contain any cracks which run from one edge to another (see Figure 4.6).

Figure 4.6: Examples of Crack-Free Particles and their Number Assessment



In the particle count, all particles wholly contained within the area of the mask shall be counted as one particle each and all the particles which are partially within the mask shall be counted as half particle each (see Figure 4.7 to 4.9).

Figure 4.7: Select Area of Coarsest Fracture






Figure 4.8: Count Perimeter Fragments as 1/2



e.g.: Number of Perimeter Particles = 32/2=16

Figure 4.9: Count Central Fragments and Add to Perimeter Count to Obtain Final Count



e.g.: Number of central fragments = 53, hence total fragments = 16 + 53 = 69

4.2.7.4 Minimum Values from the Particle Count

In order to classify a glass as a fully toughened safety float glass, the particle count of each test specimen shall not be less than the values given in Table 4.7.

Table 4.7: Minimum Particle Count

Glass Type	Nominal Thickness (mm)	Minimum Particle Count
Float and Drawn Sheet	3	15
	4 to 12	40
	15 to 19	30
Patterned	4 to 10	30

4.2.8 Stress Measurement Test

4.2.8.1 General


Stress measurement is a non-destructive test to check the toughening properties of fully toughened safety float glass. The specimens are examined by the polariscopic or light refraction methods¹³ for surface or edge compression. When the range of the apparatus permits examination for edge compression only, obtain the averaged value for all midpoints of every edge.

4.2.8.2 Test Procedure

¹³ The most common apparatus to conduct this test is the GASP instrument by Strainoptics Inc. Other methods like DSR may also be used.

Two surface compression measurements shall be made in each of five locations, oriented in two directions at 90° to each other, for a total of ten readings on each specimen to be tested. Average the ten readings to determine the stress level of the test sample. The five locations to be examined are shown in Fig. 4.10.

Figure 4.10: Five Points to be Examined



4.2.8.3 Assessment of Measurements

Fully toughened glass shall have either a minimum surface compression of 69 MPa (10,000 psi) or an edge compression of not less than 67 MPa (9,700 psi).

4.2.9 Marking

Logo position from corner edge (preferably bottom-right) should be preferably 25mm ± 5mm. All float toughened glass should have mark 'TF' along with brand name.

4.3 Other Physical Characteristics

4.3.1 Anisotropy (Iridescence)

Heat-treated glass (heat-strengthened or tempered) can have an optical phenomenon that is called strain pattern or quench pattern. This phenomenon can appear as faint spots, blotches, or lines. This is the result of the air quenching (cooling) of the glass when it is heat-treated and should not be considered a glass defect.

The heat treatment process results in a higher surface compression directly opposite the air quench, air nozzles or slots. The higher compression areas are denser and can exhibit a darker appearance under some viewing conditions especially when light is polarized, such as a skylight or other forms of reflected light. The colors of the strain pattern are sometimes referred to as iridescent, or the general condition as iridescence. The pattern that is seen under certain lighting conditions may vary from manufacturer, depending on the design of the cooling apparatus. The intensity of the quench or strain pattern is influenced by the viewing angle, lighting conditions and by the perceptiveness of the viewer. It is nearly impossible to eliminate the strain pattern or quench pattern in heat treated glass products.

The presence of a strain pattern or the perceivable differences in the strain pattern is not a glass defect or blemish and is not cause for rejection. In addition, the presence of a strain pattern does not alter the structural integrity or safety of the glass lite.

When viewing from the interior of the building, the quench pattern may be visible from a 10° viewing angle and not apparent at a 90° viewing angle from the surface of the glass. When viewing the glass in reflectance from the exterior of the building, the quench pattern may be visible when looking at the glass surface at a 30-60° angle. Visibility of the quench pattern may be accentuated with thicker glass, tinted glass substrates, coated glass and multiple lites of heat-treated glass in laminated or insulating glass products.

Construction sites may yield viewing angles and conditions that cause the quench pattern to become visible. However, upon completion of construction; the presence of interior walls; finishes; furniture; and plants frequently results in the strain pattern being less visible or not visible at all.

The stresses introduced in the heat-treating of glass are an inherent part of the fabrication process, and while they may be affected or altered depending on the heating process, controls and/or quench design, they cannot be eliminated. Design professionals should be aware that quench patterns are not a defect in heat-treated glass and, therefore, are not a basis for product rejection.

4.3.2 Spontaneous Breakage due to Nickel Sulphide Inclusions

In various situations fully tempered glass may break for no reason. Many factors might cause such spontaneous breakages, but the most common are nickel sulphide inclusions. Nickel sulphide inclusion, also known as NiS, occurs during the manufacturing process for float glass. In the glass batch, nickel-rich contaminants such as stainless steel might be present, and then combine with sulphur to form nickel sulphide inclusions.

Nickel sulfide is an interesting compound that exists in different phases at different temperatures. Two specific phases of NiS exist, known as the alpha-phase and the beta-phase. At temperatures below 380°C (715 F), nickel sulfide is stable in the beta-phase. Above this temperature, it is stable in the alpha-phase. Therefore, when glass is produced in the furnace, it is overwhelmingly likely that any NiS inclusions will be in the alpha-phase. In typical annealed glass, the slow cooling process provided by the annealing lehr allows the NiS ample time to transform to its beta-phase as the glass cools. However, in the fast cooling process used in both heat-strengthened and tempered glass, there is insufficient time to complete the phase transition (which is a relatively slow process). The inclusions therefore are "trapped" in the glass in their high-temperature alpha-phase.

However, once the glass cools past the phase change temperature, the NiS inclusion seeks to reenter its lower

energy beta-phase. For “trapped” inclusions, this process takes anywhere from months to years. When NiS changes from alpha-phase to beta-phase, it increases in volume by 2 to 4%. This expansion creates localized tensile stresses that are estimated to be as much as 125,000 psi (860 MPa) at the glass-NiS interaction surface. The magnitude of this stress drops off sharply away from the face of the inclusion, but is sufficient at the face to cause microcracking.

In the core tension zone of the glass, these microcracks are propagated by stress concentrations at the tip of the crack until the structure of the glass is undermined completely and the tempered glass undergoes its characteristic shattering, which causes the seemingly spontaneous failure. It is important to understand that since there is no data available worldwide on the amount of NiS inclusions that could occur, breakage due to NiS suicide is a property, and not a defect in tempered glasses.

5. Heat-Strengthened Glass

5.1 Manufacturing Process

Heat-strengthened glass is produced when float glass panels are heated and then cooled gradually in a controlled environment. This process makes the glass stronger than annealed glass. Since the cooling is more gradual, the stresses formed in heat-strengthened glass is less than that of fully tempered glass. Heat-strengthened glasses are two times stronger than annealed glasses. They break into relatively large fragments that stick to its glazing framework when broken. Heat-strengthened glasses are not classified as a safety glazing material.

5.2 Quality Parameters

5.2.1 Thickness

The thickness tolerance of toughened glasses shall be in accordance with the tolerances mentioned for annealed float glasses. Please refer Table 2.1 for details.

5.2.2 Dimensions and Squareness

Tolerance limits for dimensions for rectangular glass panes are given in Figure 1 and tolerances on width and length should be in accordance with Table 5.1.

Figure 5.1: Tolerance Limits for Dimensions of Rectangular Panes




Table 5.1: Tolerances on Width B and Length H

(All dimensions are in millimeters and as per EN12150-1 June 2000)

Nominal Dimension of Side, B or H	Tolerance, t	
	Nominal Glass Thickness $d \leq 12$	Nominal Glass Thickness $d > 12$
≤ 2000	2.5	3.0
$2000 < B \text{ or } H \leq 3000$	3.0	4.0
> 3000	4.0	5.0

5.2.3 Holes and Cutouts¹⁴

5.2.3.1 Hole Dimensions

The allowable hole diameter tolerance should be in accordance with Table 5.2.

Table 5.2: Tolerances on Holes

(All dimensions are in millimeters)

	Hole Diameter Range	Dimensional Tolerance
All Thicknesses	4 to 20	± 1
	21 to 100	± 2
	Above 100	Consult the Manufacturer

5.2.3.2 Hole and Cutout Location

The allowed hole and cutout location tolerance should be in accordance with Table 5.3.

Table 5.3: Tolerances on Hole and Cutout Location

(All dimensions are in millimeters)

All Thicknesses	For holes tolerance should be from centre of hole	$\pm 1.5\text{mm}$
	For cutouts tolerance should be from edge	$\pm 1.5\text{mm}$

5.2.4 Glass Edge Finish

Edge damage usually occurs when cutting the glass (difficulty increases with thickness) and during grinding of glass. There is no standard acceptance criteria for the edge condition of the glass. Glass with edges that are severely cut, damaged or have deep, pointed shells/vents is generally not acceptable. The glass edge finish should be in accordance with Table 5.4.

Table 5.4: Glass Edge Finish

SNo.	Usage Type	Finish	Allowable Defects
1	Exposed edges	Neatly polished, straight line	Small glass fragment normally conchoidal $\leq 2\text{mm}$
2	Silicon or butt joint	Visible line should be straight	Small glass fragment normally conchoidal $\leq 2\text{mm}$
3	Concealed edge	Rough grinding without chips and defects	Small glass fragment normally conchoidal $\leq 3\text{mm}$

5.2.5 Flatness

5.2.5.1 General Information

By the very nature of the toughening process, it is not possible to obtain a product as flat as annealed glass. The difference depends on the nominal thickness, the glass

¹⁴ Please note that since it does not have a high compressive strength, it is not recommended to drill holes and cutouts in heat-strengthened glasses.

size dimensions and the ratio between the dimensions. Therefore a distortion known as overall bow can occur. There are two kinds of bow (see Figure 4.3):

- overall or general bow
- local bow

NOTE 1: Overall bow can, in general, be accommodated by the framing system.


NOTE 2: Local bow needs to be allowed for in the glazing materials and the weather seals. For special requirements the manufacturers should be consulted.

5.2.5.2 Measurement of Overall Bow

The pane of glass shall be placed in a vertical position and supported on its longer side by two load bearing blocks at the quarter points (see Figure 5.2). The deformation shall be measured along the edges of the glass and along the diagonals, as the maximum distance between a straight metal ruler, or a stretched wire, and the concave surface of the glass (see Figure 5.3). The measurement should be done at room temperature.


The value for the bow is then expressed as the deformation, in millimeters, divided by the measured length of the edge of the glass, or diagonal, in millimeters, as appropriate.

Figure 5.2: Support Conditions for Measurement of Overall Bow



- (1) B or H
- (2) (B or H)/2
- (3) (B or H)/4
- (4) maximum 100mm

Figure 5.3: Representation of Overall and Local Bow



- (1) deformation for calculating overall bow
- (2) B or H, or diagonal length
- (3) local bow
- (4) 300mm length

5.2.5.3 Warpage and Bow Tolerances

5.2.5.3.1 Overall bow Tolerances

The allowed warpage or overall bow tolerance should be in accordance with Table 5.5.

Table 5.5: Overall Bow (Bend) Tolerance Limit

Thick-ness	Up to 1.2 m	1.2 to 2.5 m	2.5 to 3.05 m	3.05 to 3.66 m	Above 3.66 m
4mm	4mm	4mm	6mm	NA	-
5mm	3mm	4mm	5mm	7mm	-
6mm	3mm	4mm	5mm	7mm	-
8mm	3mm	4mm	5mm	6mm	10 mm
10mm	3mm	4mm	4mm	5mm	10mm
12mm	3mm	4mm	4mm	5mm	8mm

5.2.5.3.2 Local Bow Tolerances

Local bow can occur over relatively short distances on the edges of the glass. Local bow shall be measured over a limited length of 300mm by using a straight ruler, or a stretched wire, parallel to the edge at a distance of 25 mm from the edge of the glass (see Figure 5.3).

Local bow is expressed as millimeters / 300 mm length¹⁵.

¹⁵ For patterned glass, local bow shall be determined by using a straight ruler resting on the high points of the pattern and measuring to a high point of the pattern.

The maximum allowable values for the local bow, when measured according to 5.2.5.2, for glass without holes and/or notches and/or cutouts are given in Table 5.6¹⁶.

Table 5.6: Maximum Values for Local Bow

Toughening Process	Local Bow mm/300 mm
Horizontal	0.5

For horizontal tempering, 200mm from either edges parallel to the roller waves shall be excluded from measurement. This method of measurement may not be applicable for non-rectangular glasses, e.g., triangles and trapezoids.

5.2.5.4 Important Considerations for Optical Distortion in Heat-Strengthened Glass¹⁷

1. Pressures, exerted around the periphery of glass by the glazing system, can also alter glass flatness thereby distorting reflected images. This is true regardless of whether or not the glass is heat treated.
2. Sealed insulating glass units also exhibit distortion regardless of glass type. Air or gas, trapped in the sealed airspace between the panes, expands or contracts with temperature and barometric changes, creating a pressure differential between the airspace and the atmosphere. The glass reacts to the pressure differential by being deflected inward or outward.
3. Regardless of glass flatness, the degree of reflected distortion perceived is primarily and largely due to the characteristics or symmetry of the object being reflected. Linear objects (such as building curtain walls and telephone poles) and moving objects (such as cars) may appear distorted. Irregular and free-form objects such as trees and clouds will appear to have little perceived distortion.
4. Specified bow and warp limits may not adequately define, or control, the distortion that may become apparent after glazing. The factors, noted above, may have a larger influence on the perceived reflected distortion than that which is caused by bow and warp from the heat-treating process. Consultation with suppliers and the viewing of full-size mockups, under typical job conditions and surroundings, is highly recommended for user or architectural evaluation of the reflective distortion.

5.2.6 Appearance

For surface and body defects in clear or tinted toughened glasses refer to 2.2.6.

For accepted criteria of coated toughened glasses, refer to 3.3.4 and all conditions mentioned in Section 3: Coated

¹⁶ Source: para 4.2.8 to 4.2.8.4 from EN 12150-1 pages 9 to 12.

¹⁷ Source: para 7.4.3 to 7.4.6 from ASTM C 1048 - 04.

¹⁸ The most common apparatus to conduct this test is the GASP instrument by Strainoptics Inc. Other methods like DSR may also be used.

¹⁹ Heat strengthening of glass thicker than 6 mm (1/4 in.) within narrow limits of surface compression is difficult. Consult manufacturer.

Glass.

5.2.7 Stress Measurement Test


5.2.7.1 General

Stress measurement is a non-destructive test to check the toughening properties of fully toughened safety float glass. The specimens are examined by the polariscopic or light refraction methods¹⁸ for surface or edge compression. When the range of the apparatus permits examination for edge compression only, obtain the averaged value for all midpoints of every edge.

5.2.7.2 Test Procedure

Two surface compression measurements shall be made in each of five locations, oriented in two directions at 90° to each other, for a total of ten readings on each specimen to be tested. Average the ten readings to determine the stress level of the test sample. The five locations to be examined are shown in Fig. 4.10.

Figure 5.4: Five Points to be Examined



5.2.7.3 Assessment of Measurements

Heat-strengthened glass with thicknesses of 6 mm and less¹⁹ shall have a surface compression between 24 to 52 MPa (3,500 to 7,000 psi) or an edge compression of not less than 67 MPa (9,700 psi).

5.2.8 Marking

Logo position from a corner edge (preferably bottom right) should be preferably 25mm ± 5mm. All float heat-strengthened glass should have mark 'HS' along with brand name.

5.3 Other Physical Characteristics

5.3.1 Anisotropy (Iridescence)

Heat-treated glass (heat-strengthened or tempered) can have an optical phenomenon that is called strain pattern or quench pattern. This phenomenon can appear as faint spots, blotches, or lines. This is the result of the air quenching (cooling) of the glass when it is heat-treated and should not be considered a glass defect.

The heat treatment process results in a higher surface compression directly opposite the air quench, air nozzles or slots. The higher compression areas are denser and can exhibit a darker appearance under some viewing conditions especially when light is polarized, such as a skylight or other forms of reflected light. The colors of the strain pattern are sometimes referred to as iridescent, or the general condition as iridescence. The pattern that is seen under certain lighting conditions may vary from manufacturer, depending on the design of the cooling apparatus. The intensity of the quench or strain pattern is influenced by the viewing angle, lighting conditions and by the perceptiveness of the viewer. It is nearly impossible to eliminate the strain pattern or quench pattern in heat treated glass products.

The presence of a strain pattern or the perceivable differences in the strain pattern is not a glass defect or blemish and is not cause for rejection. In addition, the

presence of a strain pattern does not alter the structural integrity or safety of the glass lite.

When viewing from the interior of the building, the quench pattern may be visible from a 10° viewing angle and not apparent at a 90° viewing angle from the surface of the glass. When viewing the glass in reflectance from the exterior of the building, the quench pattern may be visible when looking at the glass surface at a 30-60° angle. Visibility of the quench pattern may be accentuated with thicker glass, tinted glass substrates, coated glass and multiple lites of heat-treated glass in laminated or insulating glass products.

Construction sites may yield viewing angles and conditions that cause the quench pattern to become visible. However, upon completion of construction; the presence of interior walls; finishes; furniture; and plants frequently results in the strain pattern being less visible or not visible at all.

The stresses introduced in the heat-treating of glass are an inherent part of the fabrication process, and while they may be affected or altered depending on the heating process, controls and/or quench design, they cannot be eliminated. Design professionals should be aware that quench patterns are not a defect in heat-treated glass and, therefore, are not a basis for product rejection.

6. Insulated Glass

6.1 Manufacturing Process

Insulated glasses are two or more panels of glass spaced apart and hermetically sealed to form a single unit with an air or gas space between each panel. Typically the spacer is made of aluminum that is either mill-finished or painted/ anodized in different colours/finishes. Desiccants are filled inside the spacer framework to prevent condensation inside the air gap. Butyl is the most popular primary sealant that joins the spacer to both glass lites. The secondary sealant can be either silicon (used for structural glazing), or polysulphide or polyurethane (used in window glasses).

6.2 Quality Parameters

6.2.1 Thickness

Dual-pane Insulated glass units shall conform to the nominal thickness values specified in Table 6.1.

Table 6.1: Thickness Tolerance of IGU

All dimensions in millimeters

First Pane	Second Pane	IGU Thickness Tolerance
Annealed Glass	Annealed Glass	± 1.0
Annealed Glass	Toughened or Heat-Strengthened Glass	± 1.5
Toughened or Heat-Strengthened Glass	Toughened or Heat-Strengthened Glass	± 1.5

The thickness tolerances of multi-cavity insulating glass units are obtained by using the following rules:

- determine the tolerance of each composition glass/ cavity/glass in accordance with Table 6.1;
- calculate the squares of those values;
- sum all those square values;
- calculate the square root of that sum.

6.2.2 Dimensions

Tolerance limits for dimensions for rectangular glass panes are given in Figure 6.1 and tolerances on width and length should be in accordance with Table 6.2.

Figure 6.1: Tolerance Limits for Dimensions of Rectangular Insulated Glass Panes




Table 6.2: Tolerances on Width B and Length H

(All dimensions are in millimeters and as per EN12150-1 June 2000)

Nominal Dimension of Side, B or H	Tolerance, t	
	Nominal Glass Thickness $d \leq 12$	Nominal Glass Thickness $d > 12$
≤ 2000	2.5	3.0
$2000 < B \text{ or } H \leq 3000$	3.0	4.0
> 3000	4.0	5.0

6.2.3 Displacement / Mismatch

Displacement/mismatch tolerance between the two glass panes shall be in accordance with Table 6.3.

Table 6.3: Displacement and Mismatch Tolerance Limit

All Thickness	All Available Range of Dimensions	± 2.0
---------------	-----------------------------------	-------

6.2.4 Glass Edge Finish

Since most insulated glass units are used in applications where edges are either concealed or sealed with secondary sealant, it is generally not required to have glasses with polished or perfectly ground edges. In most cases arising of the edges is generally enough. However, it is recommended to have the edge finish specified as part of the quality contract with the customer.

6.2.5 Sealant Protrusion

The allowed primary sealant protrusion should be in accordance with Table 6.4²⁰.

Table 6.4: Allowed Sealant Protrusion

All Thickness	Uniform Application of Sealant	± 2.0
---------------	--------------------------------	-------

6.2.6 Appearance

For surface and body defects in insulated glass units consisting of clear or tinted glasses refer to 2.2.6.

For accepted criteria of insulated glass units consisting of coated glasses, refer to 3.3.4 and all conditions mentioned

²⁰ Although slight variations in butyl application straightness is allowed, it is absolutely critical that there are no breaks in sealant application and the line is continuous, to protect against failures of the insulated unit over its life cycle.

in Section 3: Coated Glass.

6.3 Quality Tests for Insulated Glass Raw Materials

6.3.1 Delta-T Test for Desiccant

This test is used to check the adsorption capacity of desiccants used in insulated glass units.

1. Take room temperature water in a beaker and measure its initial temperature (T_i) and quantity.
2. Add equal quantity of desiccant in milligrams (mg). Now the temperature of water will start rising automatically.
3. Wait till the temperature of water reaches the maximum value.
4. Measure the final temperature (T_f).
5. Calculate $\Delta T = T_f - T_i$. ΔT should be more than 32°C .

6.3.2 Tests for Silicon (Two-Part)

It is very important that two part sealant be checked properly to ensure well curing. Improper mixing of silicon will result in adhesion failure and eventually lead to unit failure.

6.3.2.1 Butterfly Test

The purpose of butterfly test is to check for an adequate mixing of the base and catalyst components. The test is performed by dispensing a bead of sealant on to a piece of white paper and folding the paper in half, smearing down the sealing bead. Then the paper is reopened and inspected visually. This should appear uniform in colour with no white streaks.

6.3.2.2 Peel Adhesion Test

The purpose of this test is to verify adhesion of sealant to the glass substrate. An adhesive or cohesive failure of silicon with glass substrate can result due to improper curing of silicon or bad raw material quality.

1. Clean and prime the substrate.
2. Place a piece of bond breaker tape across the flat surface.
3. Apply a bead of sealant and tool it to form a strip approximately 20 cm long, 1.5 cm wide and 6 mm thick. At least 4 cm of the sealant should be applied over the bond breaker tape.
4. After sealant cure, grasp the 4 cm tab of sealant which overlays the bond breaker tape. Pull the sealant at a 180° angle. Peel back only 1 to 2 cm of sealant leaving the remainder in place for additional testing.
5. If the sealant tears within itself and remains fully bonded to the substrate, this is called "cohesive failure". 100% cohesive failure is desirable since this indicates that the strength of adhesion is greater than the strength of cohesion.

6.3.3 Butyl Quantity Test

This test is used to calculate the minimum quantity of butyl applied on a spacer. Butyl needs to be applied on spacers in a certain minimum quantity to effectively provide a primary glass to spacer seal.

1. Take a spacer system from running production and extrude butyl under standard production conditions.
2. Remove the butyl from the spacer.

3. Measure the weight of butyl.
4. Measure the length of the spacer system.
5. Calculate the ratio (length:weight) and calculate the weight of butyl per running meter.
6. The butyl quantity should be more than or equal to 2.7 grams per side per running meter

6.3.4 Tests for Finished Insulated Glass Units

6.3.4.1 Leakage Test

The insulated glass specimen is dropped in a water tank for five minutes. There should be no bubbles appearing in the water tank and no seepage of water inside the insulated glass unit.

6.3.4.2 Dew Point Test

The dew point temperature test is used to check the humidity content in the insulated glass unit air space. A sample is cooled down until condensation (dew) forms on the interior surface. This dew point should be minimum -40°C .

6.3.4.3 Shore A Hardness Test

The insulated glass sample is cured for a total of 24 hours and a Shore A hardness meter is used to check the hardness of the cured silicon sealant. For structural silicon the Shore A hardness reading should be minimum 43.

6.4 Important Considerations for Optical Distortion in Insulated Glass

6.4.1 Interference Colouration

6.4.1.1 Brewster's Fringes

When the glass pane surfaces exhibit near perfect parallelism and the surface quality is high, the insulated glass pane shows interference coloration. These are lines varying in colour as a result of decomposition of the light spectrum. When the sun is the light source, the colours vary from red to blue. This phenomenon is not considered a defect but it is inherent to the insulated glass unit construction.

6.4.1.2 Newton Rings

This optical effect only occurs in faulty insulated glass units and occurs when the two panes of glass are touching or nearly touching in the centre. The optical effect is a series of concentric coloured rings with the centre being in the point of contact/near contact of the two panes. The rings are roughly circular or elliptical.

6.4.2 Iridescence due to Heat-Treated Glasses

Some processed glasses also show coloration inherent to the product, e.g. toughened glass and heat strengthened glass. Refer to sections 4.2.9.1 and 5.2.9.1 for details.

6.4.3 Glass Deflection due to Variations in Temperature and Barometric Pressure

Temperature variations of the space filled with air and/or gas and barometric pressure variations of the atmosphere and altitude will contract or expand the air and/or gas in the cavity and consequently deflections of the glass pane will occur, resulting in distortion of reflected images. These

deflections, which cannot be prevented, show variations over time. The magnitude depends partially on the stiffness and size of the glass panes, as well as on the width of the cavity. Small sizes, thick glasses, and/or small cavities reduce these deflections significantly.

6.4.4 External Condensation

External condensation on insulated glass units may occur either inside or outside the building. When it is inside the

building, it is principally due to high humidity in the room, together with a low outside temperature. Kitchens, bathrooms, and other high humidity areas are particularly susceptible. When it is outside the building, condensation is principally due to nocturnal heat loss of the outside glass surface by infrared radiation to a clear sky, together with high humidity, but no rain, in the outside atmosphere. These phenomena do not constitute failures of the insulating glass, but are due to atmospheric conditions.

7. Laminated Glass

7.1 Manufacturing Process

Laminated glasses are constructed using two glass lites and joining them by using an interlayer in between under temperature and high pressure. Polyvinyl butyral (PVB) is the most common form of interlayer used²¹. Interlayers can be either clear or coloured and is available in transparent, translucent or opaque form depending on requirement.

7.2 Quality Parameters

7.2.1 Nominal Thickness

The nominal thickness of laminated glass shall be the sum of the nominal thickness of constituent panes of glass and interlayer material.

The thickness of the pane shall be calculated as the mean of measurements taken at the centers of the four sides. The measurements shall be taken to an accuracy of 0.01mm and the mean is then rounded to the nearest 0.1mm. The individual measurements when rounded to the nearest 0.1mm shall also be within the limit deviation.

7.2.2 Dimensions

Tolerance limits for dimensions for rectangular glass panes are given in Figure 7.1 and tolerances on width and length should be in accordance with Table 7.1.

Figure 7.1: Tolerance Limits for Dimensions of Rectangular Panes




Table 7.1: Tolerances on Width B and Length H
(All dimensions are in millimeters and as per EN12543-5: 1998)

Limit Deviations t on Width B or Length H			
Nominal Dimension of Side, B or H	Nominal Glass Thickness d ≤ 8 mm	Nominal Glass Thickness d > 8 mm	
		Each Glass Pane < 10 mm Thickness	At Least One Glass Pane ≥ 10 mm Thickness
< 1100	+2 / -2	+2 / -2	+3 / -2.5
< 2440	+3 / -2	+3 / -2	+4 / -3
> 2440	+4 / -3	+4 / -3	+4.5 / -4

7.2.3 Displacement

Displacement is the misalignment at any one edge of the constituent glass panes making up the laminated glass. The maximum allowable displacement is as given in Table 7.2.

Table 7.2: Maximum Displacement in Laminated Glass
(All dimensions are in millimeters and as per EN12543-5: 1998)

Nominal Dimension of Side, B or H	Maximum Permissible Displacement
B, H ≤ 1000	2.0
1000 < B, H ≤ 2000	3.0
2000 < B, H ≤ 4000	4.0
B, H > 4000	5.0

7.2.4 Glass Edge Finish

Once the glass is toughened or heat-strengthened, it shall not be edge-worked after making into a laminate. These panels need to be individually worked upon before toughening and then assembled into a laminate.

For details of acceptable edge finishes refer to the relevant toughened and heat-strengthened standards (4.2.4 and 5.2.4 respectively).

7.2.5 Appearance

7.2.5.1 Common Definitions

7.2.5.1.1 Spot Defects

This type of defect includes opaque spots, bubbles and foreign bodies.

7.2.5.1.2 Linear Defects

This type of defect includes foreign bodies and scratches or grazes.

7.2.5.1.3 Other Defects

²¹ Newer forms of interlayers such as ionomers are also getting increasingly popular.

Glass defects such as vents and interlayer defects such as creases, shrinkage and streaks.

7.2.5.1.4 Opaque Spots

Visible defects in the laminated glass (for e.g., tin marks, inclusions in the glass or interlayer).

7.2.4.1.5 Bubbles

Usually air bubbles, these can be in the glass or in the interlayer.

7.2.5.1.6 Foreign Bodies

Any unwanted item introduced into the laminated glass during manufacture.

7.2.5.1.7 Scratches or Grazes

Linear damage to the outside surface of the laminated glass.

7.2.5.1.8 Vents

Sharp tipped fissures or cracks running into the glass from an edge.

7.2.5.1.9 Creases

Distortions introduced into the interlayer by folds visible after manufacture.

7.2.5.1.10 Streaks due to Interlayer Inhomogeneity:

Optical distortions in the interlayer that are caused by manufacturing defects in the interlayer, and are visible after manufacture.

7.2.5.1.11 Edge Area

For panes sizes $\leq 5\text{m}^2$ the width of the edge area is 15 mm. The edge area width is increased to 20 mm for pane sizes $> 5\text{m}^2$.

7.2.5.1.12 Vision Area

The area outside of the edge area is called as vision area.

7.2.5.2 Test Method for Inspection

The laminated glass to be observed is put in a vertical position, in front of and parallel to a matt grey screen, lit by diffused daylight or equivalent. The observer will be at a distance of 2 meters from the glass and shall observe it perpendicularly (the matt screen being on the other side of the glass). Defects that are disturbing when viewed shall be marked.

7.2.5.3 Defects in the Vision Area

7.2.5.3.1 Spot Defects in the Vision Area

When inspected according to the test method stated in 7.2.4.2, the admissibility of spot defects depends on the following:

- Size of the defect
- Frequency of the defect
- Size of the pane

²² Admissibility of spot defects in laminated glass is independent of the individual glass thickness.

- Number of panes as components of a laminated glass. This is expressed in Table 7.3.

Table 7.3: Permissible Spot Defects in the Vision Area

Size of Defect d in mm		0.5 < d ≤ 1.0	1.0 < d ≤ 3.0			
			For all Sizes	A ≤ 1	1 < A ≤ 2	2 < A ≤ 8
Number of Allowed Defects	2 Panes	No limitation, however no accumulation of defects	1	2	1 / m ²	1.2 / m ²
	3 Panes		2	3	1.5 / m ²	1.8 / m ²
	4 Panes		3	4	2 / m ²	2.4 / m ²
	≥ 5 Panes		4	5	2.5 / m ²	3 / m ²

Defects less than 0.5 mm are not considered and defects greater than 3 mm are not permitted²².

An accumulation of defects occurs if four or more defects are at a distance of < 200 mm from each other. This distance is reduced to:

- 180 mm for laminated glass consisting of three panes,
- 150 mm laminated glass consisting of 4 panes, and
- 100 mm laminated glass consisting of five or more panes.

The number of permissible defects in Table 7.1 shall be increased by 1 for each individual interlayer which is thicker than 2 mm.

7.2.5.3.2 Linear Defects in the Vision Area

When inspected according to the test method given in 7.2.4.2, the linear defects are allowed as given in Table 7.2.

Table 7.2: Number of Permissible Defects in the Vision Area

Area of Pane	Number of Permissible Defects ≥ 30 mm in Length
≤ 5 m ²	Not Allowed
5 to 8 m ²	1
> 8 m ²	2

Linear defects less than 30 mm in length are allowed.

7.2.5.4 Defects in the Edge Area for Framed Glasses

When inspected according to the test method stated in 7.2.4.2, defects which do not exceed 5 mm in diameter are permitted in the edge area. If bubbles are present, the bubbled area shall not exceed 5% of the edge area.

7.2.5.5 Vents

Vents are not permitted.

7.2.5.6 Creases and Streaks

These are not allowed in the visual area.

7.2.5.7 Defects on Edge which will not be Framed

Laminated glass is usually installed in frames; when it is unframed, its edges may be

- ground edges,
- polished edges, or
- bevelled edges.

In such conditions shells, bubbles, interlayer defects and retractions are permissible if they do not become obvious when subjected to the test method in 7.2.4.2.

7.2.6 Tests for Finished Laminated Glass Units

7.2.6.1 Sampling Plan for Laminated Safety Glass

Test specimens should be representative of standard production. Test specimens should either be specially manufactured to the test size or be cut from larger panes. Test specimen with cut edges should contain at least one edge from the original pane from which it was cut. If the final product has all its edges sealed/protected then the test specimen should also have all its edges sealed/protected.

The method of supporting the test specimen shall not cover two edges of the test specimen. If the test specimen is cut from a larger pane at least one original edge shall not be covered.

Inspect the samples prior to the test at a distance between 30 cm and 50 cm in front of a white diffuse background. Only samples free of faults (bubbles, delamination, cloudiness) shall be used for the test.

7.2.6.2 Boil Test

7.2.6.2.1 Principle

This test is used to determine whether the laminated safety glass will withstand exposure to high temperatures over an extended period of time without its properties being substantially altered.

7.2.6.2.2 Procedure

Three test specimens of size 100 X 300 mm shall be used.

Immerse all the three test specimens vertically, supported on its edge²³, first in water at $65 \pm 2^\circ\text{C}$ for three minutes and then immediately in boiling water for two hours.

7.2.6.2.3 Interpretation of Results

The samples are removed from the boiling water bath and inspected between 30 and 50 cm in front of a white diffuse background.

Record the number and extent of the faults occurring in the interlayer (bubbles, delamination and cloudiness, but not discolouration) for each test specimen. Disregard all faults within 15 mm from an original edge and 25 mm from a cut edge²⁴.

Delamination taken as a criterion for evaluation after the boil test, may be described as essentially a two dimensional phenomena, in the interface between the glass and the interlayer, in which area no adhesion exists.

7.2.6.2.4 Acceptance Criteria

No faults (bubbles, delamination, cloudiness) shall be found in the three test specimens, as per the interpretation criteria mentioned in 7.2.5.1.3. If faults are found in only one test specimen, a further test may be carried out on three new test specimens, in which case no faults shall be found in any of these test specimens.

7.2.6.3 Humidity Test

7.2.6.3.1 Principle

This test is used to determine whether the laminated safety glass will withstand exposure to atmospheric humidity over an extended period of time without its properties being substantially altered.

7.2.6.3.2 Procedure

Three test specimens of size 100 X 300 mm shall be used.

Keep all the three test specimens vertically, supported on its edge²⁵, over water in a closed container. The air temperature within the container should be maintained within the limits of 50°C ²⁶.

7.2.6.3.3 Interpretation of Results

The samples are removed from the boiling water bath and inspected between 30 and 50 cm in front of a white diffuse background.

Record the number and extent of the faults occurring in the interlayer (bubbles, delamination and cloudiness, but not discolouration) for each test specimen. Disregard all faults within 15 mm from an original edge, 25 mm from a cut edge or 10 mm from any crack²⁷.

Delamination taken as a criterion for evaluation after the humidity test, may be described as essentially a two dimensional phenomena, in the interface between the glass and the interlayer, in which area no adhesion exists.

7.2.6.3.4 Acceptance Criteria

²³ The specimen shall be kept in the vessel of boiling water in such a way as not to touch the bottom of the testing vessel directly. A suitable arrangement may be used.

²⁴ If wire or mesh inlays are used, individual bubbles in the immediate vicinity of inlaid wires are permissible.

²⁵ The specimen shall be kept in the vessel of boiling water in such a way as not to touch the bottom of the testing vessel directly. A suitable arrangement may be used.

²⁶ These conditions give a relative humidity of about 100% and will lead to water condensation on the surface of the test specimen.

²⁷ If wire or mesh inlays are used, individual bubbles in the immediate vicinity of inlaid wires are permissible.

No faults (bubbles, delamination, cloudiness) shall be found in the three test specimens, as per the interpretation criteria mentioned in 7.2.5.2.3. If faults are found in only one test specimen, a further test may be carried out on three new test specimens, in which case no faults shall be found in any of these test specimens.

7.2.6.4 Fracture and Adhesion Test

7.2.6.4.1 Principle

The purpose of this test is to test the integrity of the laminated glass sample when subjected to external forced impact. The laminated safety glass is given a sudden punch and fragments from the under-surface are collected and weighed.

7.2.6.4.2 Procedure

A hardened steel wall with a diameter of 38 mm and weighing about 225 g shall be used for the test. A square hard wood frame shall be constructed so that when the test specimen rests symmetrically on the frame, 290 X 290 mm of the specimen shall remain unsupported. The frame shall be rigidly mounted on a 12 mm steel plate and the screws or bolts used for attaching it to the steel plate shall not project below the under-surface of the plate. The complete frame shall stand upon a substantial concrete bed.

A means for dropping the ball freely from a height of 4.88 meters shall be provided such that it strikes the specimen within 25 mm from its centre²⁸.

Ten specimens of 300 X 300 mm shall be tested. Prior to the test each specimen shall be weighed. The specimens shall be kept at $27 \pm 2^{\circ}\text{C}$ for four hours immediately preceding the test. Each specimen in turn shall be supported on the wooden frame in such a way that the plane of the test specimen when in the frame shall be substantially horizontal. The ball shall be dropped as described above. The fragments from the under-surface of each specimen shall be separately collected and weighed.

7.2.6.4.3 Acceptance Criteria

The test specimens shall be deemed acceptable if out of the ten specimens tested:

1. the number of specimens shown to be pierced²⁹ in the test does not exceed four, of which not more than two are brittle³⁰, and
2. if the total weight of the fragments from the underside of the unpierced specimens does not exceed 0.5 percent of the total weight of these unpierced specimens, and
3. if no unpierced specimen yields any fragment which individually weighs more than 0.5 grams.

²⁸ An electro-magnet may conveniently be used for this purpose.

²⁹ The specimen will be deemed to have been pierced if a split or tear exceeding 38 mm in length develops in the interlayer.

³⁰ A pierced specimen shall be deemed to be brittle if the breaks into two or more large pieces, or if the fracture is sufficient to allow the ball to pass through.

Notes

Notes

Closing Note

This *Quality Standards Manual* is intended to serve as a single-point quality reference guide for glass processors, aluminum fabricators, facade consultants, architects and developers. While formulating these guidelines we have looked upon various relevant world standards in existence and have based our tolerances considering a pragmatic approach on both the manufacturing and installation fronts. Wherever possible, we have used the most stringent limits from available standards, which will facilitate dispute resolution when required.

Although detailed attention has been given to ensure that this manual is complete and comprehensive in all respects, we invite suggestions for improving this guide and make it more workable for manufacturing and installation purposes. Please do write to us and we shall incorporate your valuable suggestions in the forthcoming editions.

Tariq Kachwala

*Hon. General Secretary, Federation of Safety Glass
Mumbai
July 2012*

References

- IS 2553 (Part 1) - 1990 - Safety Glass - Specification
- IS 2835 - 1987 - Specification For Flat Transparent Sheet Glass (Third Revision)
- IS 875 (Part 3) Reaffirmed 1997 - Codes For The Wind Loads
- IS 3548: 1988 - Code Of Practice For Glazing In Buildings
- IS 10439: 1983 - Code Of Practice For Patent Glazing
- IS 7760: 1985 - Specification For Steel Glass Front Cabinet
- 16CFR Chapter II (1-1-04 Edition) - Part 1201 – Safety Standards For Architectural Glazing Materials
- ANSI Z 97.1 - 1984 (R1994) - Safety Glazing Materials - Used In Buildings – Safety Performance Specifications And Methods Of Tests
- AS 2208 - 1996 - Safety Glazing Materials In Buildings
- AS 1288 - 2006 - Glass In Buildings – Selection And Installation
- BS 6206 - Part 4 - 1995 - Specifications For Impact Performance Requirements For Flat Safety Glass And Plastics For Use In Buildings
- BS 6262 - Part 4 - 1994 - Code Of Practice For Glazing For Buildings - Safety Related To Human Impact
- BS 6262 - Part 6 - 1997 - Code Of Practice For Glazing For Buildings: Special Applications
- BS 952 - For Nominal Thickness Of Glass
- BS 8000 - Part 7 - 1990 - Workmanship On Building Sites - Code Of Practice For Glazing
- BS 5516-1 - 2004 - Patent Glazing And Sloped Glazing For Buildings - Code Of Practice For Design And Installation
- BS 8213 - Part 4 - 1990 - Windows, Doors And Roof Lights: Code Of Practice For The Installation Of Replacement Windows And Door Sets In Dwellings
- BS EN 12600 - 2002 - Glass In Buildings - Pendulum Tests - Impact Test Method And Classification For Flat Glass
- BS 7499 - 1991 - Specification For Inclusion Of Glass In The Construction Of Furniture, Other Than Tables Or Trolleys, Including Cabinets, Shelving Systems And Wall Hung Or Free Standing Mirrors
- BS 7376 - 1990 - Specification For Inclusion Of Glass In The Construction Of Tables Or Trolleys
- BS EN 1727 - 1998 - Domestic Furniture, Storage Furniture, Safety Requirements And Test Method
- BS EN 1153 - 1996 - Kitchen Furniture, Safety Requirements And Test Methods For Built-in And Free Standing Kitchen Cabinets And Work Tops
- JIS R 3206 - 1997 - Tempered Glass
- JIS R 3205 - 1997 - Laminated Glass
- DIN 52337 - Methods Of Testing Flat Glass For Use In Buildings - Pendulum Impact Tests
- Glass Association Of North America Installation Guide
- Use Of Glass In Building, By Shri N.K. Garg, Scientist, Central Building Research Institute (CBRI), Rourkee
- Guidelines On Use Of Glass In Buildings-Human Safety, CCPS Publication
- JIS B 1501 Steel Balls For Ball Bearing
- JIS B 7502 Micrometer Callipers
- JIS B 7512 Steel Tape Measures
- JIS B 7516 Metal Rules
- JIS K 6301 Physical Testing Methods For Vulcanized Rubber

- JIS R 3202 Float Glass And Polished Plate Glass
- JIS R 3203 Figured Glasses
- JIS R 3204 Wired Glasses
- JIS R 3206 Tempered Glasses
- JIS R 3208 Heat Absorbing Glass
- JIS R 3212 Test Method Of Safety Glass For Road Vehicles
- JIS R 3221 Solar Reflective Glass
- JIS R 3222 Heat-strengthened Glass
- JIS Z 8401 Rules For Rounding Off Of Numerical Values
- EN 1279-1 Glass In Building – Insulating Glass Units Part 1: Generalities, Dimensional Tolerances And Rules For The System Description
- EN 1279-2: 2002 (E) - Glass In Building – Insulating Glass Units Part – 2: Long Term Test Method And Requirement For Moisture Penetration
- EN 1279-3: 2002 (E) - Glass In Building – Insulating Glass Units Part – 3: Long Term Test Method And Requirement For Gas Leakage Rate And For Gas Concentration Tolerances
- EN 1279-4: 2002 (E) - Glass In Building – Insulating Glass Units Part – 4: Methods Of Test For The Physical Attributes Of Edge Seals
- EN 1279-5: 2003 (E) - Glass In Building – Insulating Glass Units Part – 5: Evaluation Of Conformity
- EN 1279-6: 2002 (E) - Glass In Building – Insulating Glass Units Part – 6: Factory Production Control And Periodic Tests
- BS EN 12150-1:2000 - Glass In Building – Thermally Toughened Soda Lime Silicate Safety Glass
- BS EN 1863 - Glass In Building – Heat-Strengthened Soda Lime Silicate Safety Glass
- EN ISO 12543-5 – Glass In Building - Laminated Glass And Laminated Safety Glass - Dimensions And Edge Finishing
- EN ISO 12543-6 – Glass In Building - Laminated Glass And Laminated Safety Glass - Appearance

QUALITY STANDARDS MANUAL


FQSM G-101: 2012

Created: May 2012 | Version 1 | Revision 0



Federation of Safety Glass

S1/S2 2nd Floor, D2 Abhishek Tower, Alaknanda Shopping Complex, New Delhi 110 019, INDIA
info@fosg.in | www.fosg.in



FOSG-QSM/19112/VER1/REV0

Price: ₹ 100/-